

ABRASION RESISTANCE TEST DATA

SILICA JAPAN INC.

52, 1-Chome, 3-Jo, Ryokuendai, Ishikari, Hokkaido, 061-0223, Japan

TEL: +81-133-75-1710 FAX: +81-133-75-1712

silica@silicajp.com

www.silicajpworld.com



ABRASION RESISTANCE TEST DATA

CLIENT : SILICA JAPAN INC.

TESTING STANDARD : JIS K 7204 ABRASION RESISTANCE (BY WORN WEIGHT)

TEST LABORATORY : PRODUCT-GIKEN INC.

2-9-19 AKEBONO-MACHI, KOUNAN-KU, NIIGATA CITY, NIIGATA, JAPAN
(JNLA060232jp Registered Laboratory, IA Japan)

TEST DATE : 23rd OF NOVEMBER, 2011

PERSON IN CHARGE : MASAMI NAKAMARU

TEST BODY : 2 PIECES OF FLAT SAMPLE (100mm x 100mm x 5mm)

* name of the test body is given by the client

TESTING OUTLINE




TESTING MACHINE

TEST OUTLINE

TEST RESULTS (WORN VOLUME)

worn volume (g)

W/C = 40%	250SPINS	500SPINS	750SPINS	1000SPINS
1:2 MORTAR	4.8g	7.5g	9.1g	10g
1:2 MORTAR Silica White (10%)	2.9g	4.7g	5.7g	6.5g



15 NOV 2018